

**GRIPTEK ANTI-SLIP SOLUTIONS PTY LTD** 26a Production Avenue Kogarah NSW 2217 AUSTRALIA ABN: 13 622 802 797 T. 1300 01 GRIP E. info@griptek.com.au

Test Report No:	021123A		E. Ino@gnptex.com.au				
Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A							
Client:	Olympic Tiles Pty Ltd - 1265 The Horsley Drive, Wetherill Park NSW 2164						
Test Date:	2/11/2023	Temperature:	22 Deg. C				
Test Conducted to:	AS 4586:2013 Appendix A	Conducted by:	Sean C Murphy				
Test Method:	Wet Pendulum Testing	Test Device:	B.A (U Syd.), Dip. Ed Munro - Reg. No. 2015 Calibration Exp. 11/1/2025				
Surface:	G386 RD Series - 30x30cm	Rubber Slider Used:	Slider 96 (4 S Rubber)				
Slider Preparation:	Cert. No. 119/22 Abrasive paper, Grade P400 followed by pink lapping paper wet						
Test Location:	1265 The Horsley Drive, Wetherill Park NSW 2164						
Surface Preparation:	Cleaned with Water & Hand Scrubbing						
Surface Application:	N/A.						

## Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	52
2	Loose Sample	As Found	<2.0	N/A	51
3	Loose Sample	As Found	<2.0	N/A	50
4	Loose Sample	As Found	<2.0	N/A	50
5	Loose Sample	As Found	<2.0	N/A	52

Mean BPN Slip Resistance Value - SRV 51

> Classification **P4**

Contribution to Risk Low

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjuction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The

results in this test do not account for any future wear, contamination or maintenance of this surface. GripTek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected by copyright law.

Please note that this test/result is issued to you on an INDICATION ONLY basis as tests are conducted on a particular shade/production, not necessarily to material you would be receiving.

Olympic Tiles Pty Ltd will not be held responsible for the item not meeting this result.

It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.

Interpretation of the Wet Pendulum Results					
Classification of pedestrian surface materials according to the AS 4586	Mean BPN				
P5	>54				
P4	45-54				
P3	35-44				
P2	25-34				
P1	12-24				
P0	<12				

Approved Signatory: Michael Holt

ttype