



DALLAS

The Dallas range; a series of sophistication and durability.

Crafted to perfection, these glazed porcelain tiles redefine elegance while offering unmatched quality and resilience.

Featuring rectified edges giving that seamless, clean-cut look for any space

Available in:

- 300x600 Matt
- 600x600 Matt
- 1200x600 Matt – Ice only

Four Versatile Colours:

- Grey
- Ice
- Storm
- Taupe

Also Features varying faces for a diversive and stylish look in any room, commercial or residential.








Packing Information

Tile description		Quantity per Box		
Size (cm)	Texture	Pieces	Sqm	Weight (KGS)
30x60	Matt	8	1.44	28.70
60x60	Matt	4	1.44	28.70
60x120	Matt	2	1.44	37.00





Technical Specifications: DALLAS

	Properties	Test Method		Required Value		Value
	Water absorption	MS ISO 10545-3:2001		$0.5\% < E_v \leq 3\%$		2.3%
				Individual maximum 3.3%		2.0%~2.5%
	Determination of dimensions	Length and width The deviation, of the average size for each tile from the work size	MS ISO 10545-2:2002	N≥15cm	±0.3%	0~+0.02%
					±1.0mm	0~+0.2mm
		Thickness The deviation of the average thickness of each tile from the work size thickness	MS ISO 10545-2:2002	N≥15cm	±5%	-0.2%~+1.4%
					±0.5mm	0~+0.1mm
Straightness of sides The maximum deviation from straightness related to the corresponding work sizes	MS ISO 10545-2:2002	N≥15cm	±0.3%	0~+0.02%		
			±0.8mm	0~+0.1mm		
Rectangularity The maximum deviation from Rectangularity related to the corresponding work sizes	MS ISO 10545-2:2002	N≥15cm	±0.3%	+0.04%~+0.06%		
			±1.5mm	+0.2mm~+0.4mm		
	Breakage strength	MS ISO 10545-4:2003		≥ 1100		1353
	Modulus of rupture	MS ISO 10545-4:2003		Minimum 30		30.8
				Individual minimum 27		29.6~31.8
	Chemical resistance	a) Household chemicals: Ammonium chloride, 100g/L	MS ISO 10545-13:2018	Minimum B	A	
		b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	MS ISO 10545-13:2018	Minimum B	A	
	Stain resistance	a) Green staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
		b) Red staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
		c) Iodine, 13g/L solution in alcohol	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
		d) Olive oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
	Origin	MADE IN CHINA				

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.