



EVEREST

The Everest series brings the serenity of the mountains into your home/workplace.

This rectified glazed porcelain collection is available in three colours: Cloud, Ice & Clay.

All colours come in:

-In/Out Surface 30x30, 30x60 & 60x60 size

-Soft Polished 60x120

- 20mm thick paver 60x60 with a 40x60 pencil edged Bull nose

Offering a modern and stylish look for any space no matter what preferred style or aesthetic. The Everest is versatile and will add a touch of elegance to any space.



CLOUD



CLAY



ICE



*60x120 Soft Polished

*20mm
Bullnose

*In/Out Surface
*20mm Paver

*In/Out
Surface

*In/Out
Surface

60x120

40x60

60 X 60

30 X 60

30 X 30








Packing Information

Tile description		Quantity per Box		
Size (cm)	Texture	Pieces	Sqm	Weight (KGS)
30x30	In/Out	11	0.99	19.80
30x60	In/Out	8	1.44	28.20
60x60	In/Out	4	1.44	32.00
60x60	20mm External	2	0.72	33.85
60x120	Soft Polish	2	1.44	37.00
40x60	20mm External Bullnose	3	-	33.80












Technical Specifications: Everest 20mm

	Properties	Test Method		Required	Value
	Water absorption	ISO 10545-3:2018		$E_v \leq 0.5\%$ 单个值不大于 0.6% Individual maximum 0.6%	0.08% 0.07%~0.08%
	Determination of dimensions	长度和宽度 Length and Width 每块砖的平均尺寸相对于工作尺寸的允许偏差 The deviation of the average size for each tile (4 sides) from the work size	ISO10545-2:2018	$\pm 0.3\%$ $\pm 1.0\text{mm}$	-0.05%~-0.03% -0.3mm~ -0.2mm
		厚度 Thickness 每块砖厚度的平均值相对于工作尺寸的最大允许偏差 The deviation of the average thickness of each tile from the work size thickness	ISO10545-2:2018	$\pm 5\%$ $\pm 0.5\text{mm}$	-0.3%~+0.3% 0~ +0.1mm
		边直度 Straightness of sides 相对于工作尺寸的最大允许偏差 The maximum deviation from straightness related to the corresponding work sizes	ISO10545-2:2018	$\pm 0.3\%$ $\pm 0.8\text{mm}$	+0.01% 0~+0.1mm
		直角度 Rectangularity 相对于工作尺寸的最大允许偏差 The maximum deviation from Rectangularity related to the	ISO10545-2:2018	$\pm 0.3\%$ $\pm 1.5\text{mm}$	-0.05%~-0.02% -0.3mm~-0.1mm
	Breakage strength	ISO 10545-4:2019		≥ 1300	10155
	Modulus of rupture	ISO 10545-4:2019		平均值 ≥ 35 Minimum 35 单个值 ≥ 32 Individual minimum 32	— —
	Chemical resistance	a) 家庭化学试剂: 氯化铵溶液, 100g/L a) Household chemicals: Ammonium chloride, 100g/L	ISO 10545-13:2016	不低于 B Minimum B	A
		b) 游泳池盐类: 次氯酸钠溶液, 20mg/L b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	ISO 10545-13:2016	不低于 B Minimum B	A
	Stain resistance	a) 轻油中的铬绿 a) Green staining agent in light oil	ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		b) 轻油中的红色污染物 b) Red staining agent in light oil	ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		c) 13g/L 碘酒液 c) Iodine, 13g/L solution in alcohol	ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		d) 橄榄油 d) Olive oil	ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
	Origin	MADE IN CHINA			

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.

Technical Specifications: Everest InOut

	Properties	Test Method	Required Value	Value																																																
	Water absorption	MS ISO 10545-3:2001	$E_b \leq 0.5\%$ Individual maximum 0.6%	0.17% 0.16%~0.19%																																																
	Determination of dimensions	<table border="1"> <thead> <tr> <th colspan="2">Dimensions and surface quality</th> </tr> </thead> <tbody> <tr> <td>Length and width The deviation, of the average size for each tile from the work size</td> <td>MS ISO 10545-2:2002</td> </tr> <tr> <td>Thickness The deviation of the average thickness of each tile from the work size thickness</td> <td>MS ISO 10545-2:2002</td> </tr> <tr> <td>Straightness of sides The maximum deviation from straightness related to the corresponding work sizes</td> <td>MS ISO 10545-2:2002</td> </tr> <tr> <td>Rectangularity The maximum deviation from Rectangularity related to the corresponding work sizes</td> <td>MS ISO 10545-2:2002</td> </tr> </tbody> </table>	Dimensions and surface quality		Length and width The deviation, of the average size for each tile from the work size	MS ISO 10545-2:2002	Thickness The deviation of the average thickness of each tile from the work size thickness	MS ISO 10545-2:2002	Straightness of sides The maximum deviation from straightness related to the corresponding work sizes	MS ISO 10545-2:2002	Rectangularity The maximum deviation from Rectangularity related to the corresponding work sizes	MS ISO 10545-2:2002	<table border="1"> <tbody> <tr> <td rowspan="2">N≥15cm</td> <td>±0.6%</td> <td>0~+0.01%</td> </tr> <tr> <td>±2.0mm</td> <td>0~+0.1mm</td> </tr> <tr> <td rowspan="2">N≥15cm</td> <td>±5%</td> <td>+0.4%~+1.7%</td> </tr> <tr> <td>±0.5mm</td> <td>0 ~+0.2mm</td> </tr> <tr> <td rowspan="2">N≥15cm</td> <td>±0.5%</td> <td>-0.01%~+0.01%</td> </tr> <tr> <td>±1.5mm</td> <td>-0.1mm~+0.1mm</td> </tr> <tr> <td rowspan="2">N≥15cm</td> <td>±0.5%</td> <td>-0.06%~+0.08%</td> </tr> <tr> <td>±2.0mm</td> <td>-0.4mm~+0.5mm</td> </tr> </tbody> </table>	N≥15cm	±0.6%	0~+0.01%	±2.0mm	0~+0.1mm	N≥15cm	±5%	+0.4%~+1.7%	±0.5mm	0 ~+0.2mm	N≥15cm	±0.5%	-0.01%~+0.01%	±1.5mm	-0.1mm~+0.1mm	N≥15cm	±0.5%	-0.06%~+0.08%	±2.0mm	-0.4mm~+0.5mm																			
Dimensions and surface quality																																																				
Length and width The deviation, of the average size for each tile from the work size	MS ISO 10545-2:2002																																																			
Thickness The deviation of the average thickness of each tile from the work size thickness	MS ISO 10545-2:2002																																																			
Straightness of sides The maximum deviation from straightness related to the corresponding work sizes	MS ISO 10545-2:2002																																																			
Rectangularity The maximum deviation from Rectangularity related to the corresponding work sizes	MS ISO 10545-2:2002																																																			
N≥15cm	±0.6%	0~+0.01%																																																		
	±2.0mm	0~+0.1mm																																																		
N≥15cm	±5%	+0.4%~+1.7%																																																		
	±0.5mm	0 ~+0.2mm																																																		
N≥15cm	±0.5%	-0.01%~+0.01%																																																		
	±1.5mm	-0.1mm~+0.1mm																																																		
N≥15cm	±0.5%	-0.06%~+0.08%																																																		
	±2.0mm	-0.4mm~+0.5mm																																																		
	Breakage strength	MS ISO 10545-4:2003	≥1300	1899																																																
	Modulus of rupture	MS ISO 10545-4:2003	Minimum 35 Individual minimum 32	39.3 37.2~41.1																																																
	Chemical resistance	<table border="1"> <thead> <tr> <th colspan="4">Resistance to chemicals</th> </tr> </thead> <tbody> <tr> <td colspan="4">Resistance to household chemicals and swimming pool salts</td> </tr> <tr> <td>a) Household chemicals: Ammonium chloride, 100g/L</td> <td>MS ISO 10545-13:2018</td> <td>Minimum GB</td> <td>A</td> </tr> <tr> <td>b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L</td> <td>MS ISO 10545-13:2018</td> <td>Minimum GB</td> <td>A</td> </tr> <tr> <td colspan="4">Resistance to low concentrations of acids and alkalis</td> </tr> <tr> <td>a) Hydrochloric acid solution, 3% (v/v)</td> <td>MS ISO 10545-13:2018</td> <td>Manufacturer to state classification</td> <td>LA</td> </tr> <tr> <td>b) Citric acid solution, 100g/L</td> <td>MS ISO 10545-13:2018</td> <td>Manufacturer to state classification</td> <td>LA</td> </tr> <tr> <td>c) Potassium hydroxide, 30g/L</td> <td>MS ISO 10545-13:2018</td> <td>Manufacturer to state classification</td> <td>LA</td> </tr> <tr> <td colspan="4">Resistance to high concentrations of acids and alkalis</td> </tr> <tr> <td>a) Hydrochloric acid solution, 18% (v/v)</td> <td>MS ISO 10545-13:2018</td> <td>Test method available</td> <td>HA</td> </tr> <tr> <td>b) Lactic acid, 5 % (v/v)</td> <td>MS ISO 10545-13:2018</td> <td>Test method available</td> <td>HA</td> </tr> <tr> <td>c) Potassium hydroxide, 100g/L</td> <td>MS ISO 10545-13:2018</td> <td>Test method available</td> <td>HA</td> </tr> </tbody> </table>			Resistance to chemicals				Resistance to household chemicals and swimming pool salts				a) Household chemicals: Ammonium chloride, 100g/L	MS ISO 10545-13:2018	Minimum GB	A	b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	MS ISO 10545-13:2018	Minimum GB	A	Resistance to low concentrations of acids and alkalis				a) Hydrochloric acid solution, 3% (v/v)	MS ISO 10545-13:2018	Manufacturer to state classification	LA	b) Citric acid solution, 100g/L	MS ISO 10545-13:2018	Manufacturer to state classification	LA	c) Potassium hydroxide, 30g/L	MS ISO 10545-13:2018	Manufacturer to state classification	LA	Resistance to high concentrations of acids and alkalis				a) Hydrochloric acid solution, 18% (v/v)	MS ISO 10545-13:2018	Test method available	HA	b) Lactic acid, 5 % (v/v)	MS ISO 10545-13:2018	Test method available	HA	c) Potassium hydroxide, 100g/L	MS ISO 10545-13:2018	Test method available	HA
Resistance to chemicals																																																				
Resistance to household chemicals and swimming pool salts																																																				
a) Household chemicals: Ammonium chloride, 100g/L	MS ISO 10545-13:2018	Minimum GB	A																																																	
b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	MS ISO 10545-13:2018	Minimum GB	A																																																	
Resistance to low concentrations of acids and alkalis																																																				
a) Hydrochloric acid solution, 3% (v/v)	MS ISO 10545-13:2018	Manufacturer to state classification	LA																																																	
b) Citric acid solution, 100g/L	MS ISO 10545-13:2018	Manufacturer to state classification	LA																																																	
c) Potassium hydroxide, 30g/L	MS ISO 10545-13:2018	Manufacturer to state classification	LA																																																	
Resistance to high concentrations of acids and alkalis																																																				
a) Hydrochloric acid solution, 18% (v/v)	MS ISO 10545-13:2018	Test method available	HA																																																	
b) Lactic acid, 5 % (v/v)	MS ISO 10545-13:2018	Test method available	HA																																																	
c) Potassium hydroxide, 100g/L	MS ISO 10545-13:2018	Test method available	HA																																																	
	Stain resistance	<table border="1"> <tbody> <tr> <td>a) Green staining agent in light oil</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> <tr> <td>b) Red staining agent in light oil</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> <tr> <td>c) Iodine, 13g/L solution in alcohol</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> <tr> <td>d) Olive oil</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> </tbody> </table>			a) Green staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	b) Red staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	c) Iodine, 13g/L solution in alcohol	MS ISO 10545-14:2018	Minimum Class 3	Class 5	d) Olive oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5																																
a) Green staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5																																																	
b) Red staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5																																																	
c) Iodine, 13g/L solution in alcohol	MS ISO 10545-14:2018	Minimum Class 3	Class 5																																																	
d) Olive oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5																																																	
	Origin	MADE IN CHINA																																																		

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.