

## **GRIPTEK ANTI-SLIP SOLUTIONS PTY LTD**

26a Production Avenue Kogarah NSW 2217 AUSTRALIA ABN: 13 622 802 797

T. 1300 01 GRIP E. info@griptek.com.au

Test Report No: 191219B

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client: Olympic Tiles Pty Ltd - 1265 The Horseley Drive Wetherill Park NSW 2164

Test Date: 19-12-2019 Temperature: 30 Deg C.

Test Conducted to: AS 4586:2013 Appendix A Conducted by: Seaf Murphy

Test Method: Wet Pendulum Testing Test Device: Marro S/N 1509

Surface: Harmony Cloud Rubber Slider Used: Slider 96 (4 S Rubber)

Shaded Cloud Glazed Rectified Matt - 60x120cm

Slider Preparation: Abrasive paper, Grade P400 followed by pink lapping paper wet

Test Location: 1265 The Horsley Drive Wetherill Park NSW 2164

Surface Preparation: Cleaned with Water & Scrubbing

Surface Application: N/A.

## Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	37
2	Loose Sample	As Found	<2.0	N/A	36
3	Loose Sample	As Found	<2.0	N/A	36
4	Loose Sample	As Found	<2.0	N/A	37
5	Loose Sample	As Found	<2.0	N/A	36

Mean BPN Slip Resistance Value - SRV 36

Classification P3

Contribution to Risk Moderate

Interpretation of the Wet Pendulum Results					
Classification of pedestrian surface materials according to the AS 4586	Mean BPN				
P5	>54				
P4	45-54				
P3	35-44				
P2	25-34				
P1	12-24				
P0	<12				

teyou

Approved Signatory: Michael Holt

for use, we recommend that this report be read in conjuction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. GripTek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected