



CALIFORNIA



Elevate your floorspace with the essence of coastal charm and modern sophistication with our stunning glazed porcelain California series. Crafted with meticulous attention to detail and superior craftsmanship, these tiles are designed to redefine luxury living

Available in:

- 300x600 matt
- 600x600 matt & polished

Unique wavy Pattern

- 600x600 Polished variant features a captivating wavy pattern, adding depth and dimension to your floors.

Stylish Colour Options:

- Available in two captivating shades, Storm & Cloud.

Rectified Edges








- Ensuring a seamless, cohesive look for any room.

Varying Faces:

- 300x600 - 16 faces
- 600x600 - 8 faces



Technical Specification Matt








	Properties	Test Method	Required	Value																				
	Water absorption	MS ISO 10545-3:2001	0.5% < E _v ≤ 3% Individual maximum 3.3%	2.3% 2.0%~2.5%																				
	Determination of dimensions	<table border="1"> <tr> <td>Length and width The deviation, of the average size for each tile from the work size</td> <td>MS ISO 10545-2:2002</td> <td>N ≥ 15cm</td> <td>±0.3% ±1.0mm</td> <td>0~+0.02% 0~+0.2mm</td> </tr> <tr> <td>Thickness The deviation of the average thickness of each tile from the work size thickness</td> <td>MS ISO 10545-2:2002</td> <td>N ≥ 15cm</td> <td>±5% ±0.5mm</td> <td>-0.2%~+1.4% 0~+0.1mm</td> </tr> <tr> <td>Straightness of sides The maximum deviation from straightness related to the corresponding work sizes</td> <td>MS ISO 10545-2:2002</td> <td>N ≥ 15cm</td> <td>±0.3% ±0.8mm</td> <td>0~+0.02% 0~+0.1mm</td> </tr> <tr> <td>Rectangularity The maximum deviation from Rectangularity related to the corresponding work sizes</td> <td>MS ISO 10545-2:2002</td> <td>N ≥ 15cm</td> <td>±0.3% ±1.5mm</td> <td>+0.04%~+0.06% +0.2mm~+0.4mm</td> </tr> </table>	Length and width The deviation, of the average size for each tile from the work size	MS ISO 10545-2:2002	N ≥ 15cm	±0.3% ±1.0mm	0~+0.02% 0~+0.2mm	Thickness The deviation of the average thickness of each tile from the work size thickness	MS ISO 10545-2:2002	N ≥ 15cm	±5% ±0.5mm	-0.2%~+1.4% 0~+0.1mm	Straightness of sides The maximum deviation from straightness related to the corresponding work sizes	MS ISO 10545-2:2002	N ≥ 15cm	±0.3% ±0.8mm	0~+0.02% 0~+0.1mm	Rectangularity The maximum deviation from Rectangularity related to the corresponding work sizes	MS ISO 10545-2:2002	N ≥ 15cm	±0.3% ±1.5mm	+0.04%~+0.06% +0.2mm~+0.4mm		
Length and width The deviation, of the average size for each tile from the work size	MS ISO 10545-2:2002	N ≥ 15cm	±0.3% ±1.0mm	0~+0.02% 0~+0.2mm																				
Thickness The deviation of the average thickness of each tile from the work size thickness	MS ISO 10545-2:2002	N ≥ 15cm	±5% ±0.5mm	-0.2%~+1.4% 0~+0.1mm																				
Straightness of sides The maximum deviation from straightness related to the corresponding work sizes	MS ISO 10545-2:2002	N ≥ 15cm	±0.3% ±0.8mm	0~+0.02% 0~+0.1mm																				
Rectangularity The maximum deviation from Rectangularity related to the corresponding work sizes	MS ISO 10545-2:2002	N ≥ 15cm	±0.3% ±1.5mm	+0.04%~+0.06% +0.2mm~+0.4mm																				
	Breakage strength	MS ISO 10545-4:2003	≥ 1100	1353																				
	Modulus of rupture	MS ISO 10545-4:2003	Minimum 30 Individual minimum 27	30.8 29.6~31.8																				
	Chemical resistance	<table border="1"> <tr> <td>a) Household chemicals: Ammonium chloride, 100g/L</td> <td>MS ISO 10545-13:2018</td> <td>Minimum B</td> <td>A</td> </tr> <tr> <td>b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L</td> <td>MS ISO 10545-13:2018</td> <td>Minimum B</td> <td>A</td> </tr> </table>	a) Household chemicals: Ammonium chloride, 100g/L	MS ISO 10545-13:2018	Minimum B	A	b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	MS ISO 10545-13:2018	Minimum B	A														
a) Household chemicals: Ammonium chloride, 100g/L	MS ISO 10545-13:2018	Minimum B	A																					
b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	MS ISO 10545-13:2018	Minimum B	A																					
	Stain resistance	<table border="1"> <tr> <td>a) Green staining agent in light oil</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> <tr> <td>b) Red staining agent in light oil</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> <tr> <td>c) Iodine, 13g/L solution in alcohol</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> <tr> <td>d) Olive oil</td> <td>MS ISO 10545-14:2018</td> <td>Minimum Class 3</td> <td>Class 5</td> </tr> </table>	a) Green staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	b) Red staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	c) Iodine, 13g/L solution in alcohol	MS ISO 10545-14:2018	Minimum Class 3	Class 5	d) Olive oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5						
a) Green staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5																					
b) Red staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5																					
c) Iodine, 13g/L solution in alcohol	MS ISO 10545-14:2018	Minimum Class 3	Class 5																					
d) Olive oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5																					
	Origin	MADE IN CHINA																						

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.

Packing Information

Tile description		Quantity per Box		
Size (cm)	Texture	Pieces	Sqm	Weight (KGS)
30x60	Matt	8	1.44	25.90
60x60	Matt & Polished	4	1.44	25.90

Technical Specification Polish

	Properties	Test Method		Required Value	Value
	Water absorption	EN ISO 10545-3:2018		$E_b \leq 0.5\%$ 单个值不大于 0.6% Individual maximum 0.6%	0.05% 0.04% ~ 0.06%
	Determination of Dimensions	长度和宽度 Length and Width 每块砖的平均尺寸相对于工作尺寸的允许偏差 The permissible deviation of the average size for each tile (4 sides) from the work size EN ISO 10545-2:2018	$\pm 0.6\%$ $\pm 2.0\text{mm}$	$-0.06\% \sim -0.03\%$ $-0.3\text{mm} \sim -0.2\text{mm}$	
		厚度 Thickness 每块砖厚度的平均值相对于工作尺寸的最大允许偏差 The permissible deviation, of the average thickness of each tile from the work size thickness EN ISO 10545-2:2018	$\pm 5\%$ $\pm 0.5\text{mm}$	$-0.6\% \sim +0.6\%$ $-0.1\text{mm} \sim +0.1\text{mm}$	
	Breakage strength	EN ISO 10545-4:2019		≥ 1300	2418
	Modulus of rupture	EN ISO 10545-4:2019		平均值 ≥ 35 Minimum 35 单个值 ≥ 32 Individual minimum 32	48.8 47.0 ~ 50.4
	Chemical resistance	家庭化学试剂: 氯化铵溶液, 100g/L a) Household chemicals: Ammonium chloride, 100g/L EN ISO 10545-13:2016	不低于 B 级 Minimum class B	A	
		b) 游泳池盐类: 次氯酸钠溶液, 20mg/L b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L EN ISO 10545-13:2016	不低于 B 级 Minimum class B	A	
	Stain resistance	a) 轻油中的铬绿 a) Green staining agent in light oil	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		b) 轻油中的红色污染物 b) Red staining agent in light oil	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		c) 13g/L 碘酒液 c) Iodine, 13g/L solution in alcohol	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		d) 橄榄油 d) Olive oil	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
	Origin	MADE IN CHINA			

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.